



Tapecoat®

Technical Data Sheet

DESCRIPTION	Tapecoat TC® 7030 Epoxy is a two part, 100% solids, high build, high temperature coating designed to provide protection against corrosion on pipelines with service temperatures up to 300°F (149°C). TC 7030 is a below grade, standalone coating that can be applied by brush or applicator pad. A 25 mil coating can be applied in one application. TC 7030 is a fast curing epoxy allowing for backfill in 2-3 hours at 70°F and 50% RH.
SUBSTRATE COMPATIBILITY	Steel, Stainless Steel, Ductile Iron, Other Metals, FBE
RECOMMENDED USE	Ideal for protecting girth welds, fittings, flanges, valves, and all types of piping and metal structures. Can also be used for directional drilling when reinforced with TC Reinforcing Scrim.
SURFACE PREPARATION	SSPC SP-10/NACE No. 2/ SA 2 1/2 Near-White Blast Cleaning 2-4 mil surface profile
PRIMER	None Required
OPTIONAL REINFORCEMENT	To increase abrasion and impact resistance and for creating high coating build TC Reinforcing Scrim can be used.
REFERENCE	TC 7030 meets all of the performance criteria listed in the most recent revisions of: NACE RP0105 ANSI/AWWA C210
SAFETY	Refer to Material Safety Data Sheet: MSDS-TC7030-RESIN; MSDS-TC7030-HARDENER
APPLICATION	Refer to Application Guidelines: AG-EPOXIES

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Corporation
295 University Avenue
Westwood, MA 02090

Phone: 800-323-4182
Fax: 781-332-0701
www.chasecorp.com

An ISO 9001:2008
REGISTERED COMPANY

TYPICAL DATA

Property	US Customary	Metric	Test Method
Color	Red	Red	
Coating Thickness	25 mil	635 μ m	
VOC Content	0 lb/gal	0 g/l	
Pot Life @ 70°F (21°C), 50% RH	10-15 minutes	10-15 minutes	
Time to Backfill @ 70°F (21°C), 50% RH	2-3 Hours	2-3 Hours	
Cathodic Disbondment, 30 days	<0.2 in ²	<5 mm radial	ASTM G8
Pull Off Adhesion to Steel	>2000 psi	> 13.8 MPa	ASTM D4541 Type II
Pull Off Adhesion to FBE	>2000 psi	> 13.8 MPa	ASTM D4541 Type II
Impact Resistance	22 in*lb ^f	2.5J	ASTM G14
Shore D Hardness	85-90	85-90	ASTM D2240
Dielectric Strength	Exceeds 12 kV (25 mil)	Exceeds 12 KV (635 μ m)	ASTM D149
Holiday Detection Setting	6250 V (25 mil)	6250 V (635 μ m)	NACE RP0274
Water Absorption	<0.5%	<0.5%	ASTM D570
Water Vapor Transmission Rate	<0.01 g/(24h*100 in ²) (25 mil)	<0.05 g/(h*m ²) (635 μ m)	ASTM E96 Procedure B
Chemical Resistance	Pass	Pass	ASTM G20
Application Temperature Range	45°F to 120°F	7°C to 49°C	
Service Temperature Range	-40°F to 300°F	-40°C to 149°C	

ORDERING INFORMATION

TC 7030

Kit Size	Kits Per Case	# Per Case
Pint	4	12
Quart	2	11
Gallon	2	35

TC REINFORCING SCRIM

Roll Size	Rolls Per Case	# Per Case
2" x 100'	24	10
4" x 100'	12	10
6" x 100'	8	10